

# IPE SEAL™

END GRAIN SEALANT

## technical data sheet



### Clean Up

Use hot, soapy water on a clean brush.  
Solvents are NOT recommended.

### Directions

Apply liberally with a brush to all end cuts "to the drip". (Apply as much as the end grain will hold. If none drips off, it's probably too little. If a lot drips off, it's too much.) The sooner you apply our end sealer after exposing the end grain (and face grain of turnings and carvings), the more effective the coating will be. It is recommended that you apply our end sealer to the wood within 24hrs of cutting. This sealer is very slippery.  
\*\*DO NOT apply to walking surfaces\*\*

### About Ipe Seal™

Our End Sealer is a wax emulsion sealer designed to prevent end checking (drying splits) in freshly sawn logs, lumber, turning blanks, and other exposed wood end and face grain. Due to differences in wood species, variety of climatic conditions, and an individuals' usage methods; results are NOT guaranteed.

Treated with Ipe Seal™



Untreated End-Cut



### Advisory/Warning

Our End Sealer may cause color or shading changes in wood, depending on species, dryness, handling or other natural variables. Test on ends of sample piece(s) and let stand for 48 hours if this possibility is of concern.

### Safety

This is a non-hazardous wax emulsion.  
Treat it with the same respect as paint:  
DO NOT drink.  
DO NOT breathe the liquid.  
AVOID contact with eyes.

### Accidental Overexposure

Inhalation: Remove to fresh air and consult your physician immediately.  
Eyes: Flush well with water and consult your physician immediately.  
Ingestion: Drink 1 quart of water and see your physician for ingestion of a paraffin wax and water emulsion.  
Skin: Wash well with soap and water.

DeckWise® USA  
2111 58th Avenue East, Bradenton, FL 34203  
Local: 941-896-9851  
Toll Free: 866-427-2547

DeckWise®